



APET and UltraTuf™ PETG Sheet

Helping provide a safety barrier between people and disease.

Today more than ever there is a heightened need for increased public health and safety. Spartech plastics are meeting that demand by providing an essential solution for Personal Protective Equipment (PPE). Our APET and UltraTuf™ PETG Anti-Fog coated plastics provide a reliable and protective face shield material to help keep people free from exposure to chemicals and disease. It is also ideal for use as a barrier for safe interaction between employees and customers in retail environments as well as for food protection in restaurants.

APET and UltraTuf™ PETG material benefits:

- Anti-fog coated
- Cost-effective and easy to customize material

- FDA compliant
- Provides an employee/customer barrier at the point of sale for retailers
- Superior chemical protection and impact resistance
- Very clear and disinfects easily
- Ideal for use as a face shield or as a discardable barrier

It is safe to say Spartech has solutions for various PPE applications. To learn more about our APET and UltraTuf™ PETG anti-fog coated materials, call Spartech today at 800-677-4338 (800-67-SHEET) or e-mail info@spartech.com.

UltraTuf™ PETG Anti-Fog coated sheet

UltraTuf™ PETG (polyethylene terephthalate glycol) sheet has been developed for PPE applications such as safety visors and retail point-of-sale barriers for those who need protection without having their vision hampered. This material offers high clarity, impact resistance and is available in gauges ranging from 0.010" to 0.042".

The UltraTuf™ PETG sheet product line includes the following options:

- One side is anti-fog coated
- One side is anti-fog coated, cling poly on opposite side

APET Anti-Fog coated sheet

APET (amorphous polyethylene phthalate) sheet has been specifically developed for PPE applications that require clarity along with a good balance of stiffness and toughness. This material can be designed to comply with FDA Food Contact Regulation 21 CFR 177.1630 for polyethylene phthalate polymers.

The APET sheet product line includes the following options:

- One side anti-fog coated
- One side anti-fog coated, cling poly on opposite side
- One side anti-fog coated with anti-block in the bulk

TYPICAL PROPERTIES – APET SHEET		
PROPERTY	TEST METHOD	VALUE
Density	ASTM D792	1.33 g/cc
Intrinsic Viscosity	ASTM D4603	0.75 +/- 0.03 dL/gm
Melting Point	ASTM D3418	246 +/- 5 °C
Tensile Strength	ASTM D638	8,000 psi
Izod Impact, Notched	ASTM D256	0.50 ft-lbs/in

PET/APET meets the APR (Association of Plastic Recyclers) and California State requirements to be categorized as recyclable into RIC (Resin Identification Code) #1 recycle stream.

TYPICAL PROPERTIES – PETG SHEET		
PROPERTY	TEST METHOD	VALUE
Density	ASTM D792	1.27 g/cc
Tensile Strength	ASTM D638	7,700 psi
Flexural Modulus	ASTM D790	310,000 psi
Izod Impact, Notched, 72 °F	ASTM D256	1.70 ft-lbs/in
Izod Impact, Notched, -5 °F	ASTM D256	0.70 ft-lbs/in

11650 Lakeside Crossing Ct., Maryland Heights, MO, 63146 • 800-677-4338 • www.spartech.com

Copyright ©2020, Spartech, LLC. Spartech makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Spartech makes no warranties or guarantees respecting suitability of either Spartech's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. SPARTECH MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or product reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.