

Royalite® R552

Fire-rated sheet

Product Description

Royalite R552 is UL 94V-0 and UL94 5VA, flame retardant extruded sheet product manufactured from recycled PVC/Acrylic resin. The excellent balance of physical and mechanical properties, combined with its flame rating, make R552 an excellent, cost effective choice for a wide variety of applications in the electronics, equipment, and materials handling industries.

Technical Properties

Property	Test Method	Value*
Specific Gravity (color dependent)	ASTM D-792	1.35
Tensile Strength	ASTM D-638	5,500 psi
Flexural Strength	ASTM D-790	9,000 psi
Flexural Modulus	ASTM D-790	300,000 psi
Izod Impact (Notched) 72°F	ASTM D-256	7.5 ft-lbs/in
Rockwell Hardness (R Scale)	ASTM D-785	96
Heat Deflection Temperature (@264 psi - annealed)	ASTM D-648	150°F
Motor Vehicle Safety Standard	FMVSS 302	Passes
Flammability	UL 94 V-0	Listed @ 0.030"
Flammability	UL 94-5VA	Listed @ 0.091"

**All values based on 0.125" unless otherwise stated*

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail info@spartech.com or visit our website at www.spartech.com

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. **NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**