

SunGard SG

Polycarbonate

Product Description

SunGard® SG is a weatherable polycarbonate sheet that combines the impact strength of polycarbonate with outstanding ultra-violet (UV) stability. SunGard's unique properties make it the perfect choice for a variety of exterior sign applications. SunGard® SG is UL listed as UL746 F1 Suitable for Outdoor Use and is UL94 HB yellow card listed for white and clear products.

Technical Properties

Property	Test Method	Value
Specific Gravity	ASTM D-792	1.2
Melt flow rate (300C/1.2kg)	ASTM D-1238	6.0 g/10min
Tensile Strength	ASTM D-638	9000 PSI
Tensile Elongation at yield	ASTM D-638	6.00%
Tensile elongation at Break	ASTM D-638	120%
Flex strength	ASTM D-790	13000 PSI
Flex Modulus	ASTM D790	335000 Psi
Notched Izod at 73F	ASTM D-256	17 ft-lb/in
Rockwell Hardenss R-scale	ASTM D-785	110
Heat Deflection Temperature at 264 psi	ASTM D-648	260 F
Vicat softening temperature	ASTM D-1525	291 F
CLTE	ASTM E-831	3.8 E-5 in/in/F
Flammability	UL94- HB	Listed: UL94-HB at 0.098"
Light Transmittance (100mil)	ASTM D-1003	88 TO 90%
Haze (100mil)	ASTM D-1003	< 1%

**All values based on 0.125" unless otherwise stated*

For additional information, please contact Spartech at 800-677-4338 (800-67-SHEET), e-mail info@spartech.com or visit our website at www.spartech.com

Customers are responsible for determining whether products and information are appropriate for their use, including the evaluation of all applicable laws. Spartech LLC assumes no liability for the accuracy or completeness of information contained herein, and such information is subject to change without notice. All products supplied are subject to the standard terms and conditions of sale of Spartech LLC. **NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, IS MADE BY THIS TECHNICAL DATA SHEET. ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**